

Test Report

Photographic Activity Test according to ISO 18916:2007

Summary: The material described below has **passed** the criteria for enclosure materials defined in ISO 18916:2007 "Photographic activity test for enclosure materials".

PTS Test-Report: **33738**
Material description: **Monochrom OPP Klarsichttaschen**

Supplied by: **© Mono-C GmbH** on **23.11.2017**
Königstor 14 a, 34117 Kassel

Test Results

1. Image Interaction Test

The material shall not produce a percentage image interaction effect in the colloidal silver fade detectors greater than a relative difference of more than $\pm 20\%$ compared to the control.

Density change of control: **-0,98**
Density change of material: **-1,06** Relative difference: **9%**

2. Stain Test

The material shall not produce a mean stain in the photographic paper stain detector that is greater than the mean stain produced by the filter paper controls plus 0.08 density units.

Density change of control: **0,13**
Density change of material: **0,12** Difference: **0,01**

3. Mottle Test

The enclosure material shall not produce *easily recognizable* mottling.


Visual assessment: **Passed**

Date of testing: **18.12.2017** Sample-ID: **012-08**


Papiertechnische Stiftung, Pirnaer Straße 37, D-01809 Heidenau, Germany

*Papiertechnische Stiftung is
accredited according to
ISO/IEC 17025.*





Dipl.-Ing. Sabine Pensold
Laboratory Manager Materials Testing



Dipl.-Chem. Nicole Brandt
PAT Project Manager

