

# Test Report

## Photographic Activity Test according to ISO 18916:2007

**Summary:** The material described below has **passed** the criteria for enclosure materials defined in ISO 18916:2007 "Photographic activity test for enclosure materials".

PTS Test-Report: **33539**  
Material description: **Monosafe 90g Papier ungepuffert Nr. 1874**  
Supplied by: **© Mono-C GmbH** on **13.06.2017**  
**Königstor 14 a, 34117 Kassel**

### Test Results

#### 1. Image Interaction Test

The material shall not produce a percentage image interaction effect in the colloidal silver fade detectors greater than a relative difference of more than  $\pm 20\%$  compared to the control.

Density change of control: **-0,98**  
Density change of material: **-0,99**                      Relative difference: **1%**

#### 2. Stain Test

The material shall not produce a mean stain in the photographic paper stain detector that is greater than the mean stain produced by the filter paper controls plus 0.08 density units.

Density change of control: **0,12**  
Density change of material: **0,12**                      Difference: **0,00**

#### 3. Mottle Test

The enclosure material shall not produce *easily recognizable* mottling.

Visual assessment: **Passed**

Date of testing: **03.07.2017**

Sample-ID: **011-20**

Papiertechnische Stiftung is  
accredited according to  
ISO/IEC 17025.

Papiertechnische Stiftung, Pirnaer Straße 37, D-01809 Heidenau, Germany



Dipl.-Ing. Sabine Pensold  
Laboratory Manager Materials Testing



Dipl.-Chem. Nicole Brandt  
PAT Project Manager

